

**ASTS Profil Mühendislik ve Plastik San.ve Tic.A.S.**  
KOSB Organik Cd. No. 11  
**34953 Istanbul**  
**TURKEY**

Fürth, 22 November 2022

## TEST REPORT No. FUHLCP2022-08244

Date sample received: 11 November 2022  
Period of testing: 14 November 2022 - 22 November 2022  
Technical Director: Kerstin Scharrer

### Abbreviations:

- \* = Test method is not part of the accreditation scope
- \*\* = Outsourcing
- n.a. = not applicable
- n.t. = not tested
- n.d. = not determinable (< LoQ)
- LoQ = limit of quantification
- CS = Combined sample
- P = passed
- F = failed
- # = Subsequent delivery

### Sample description: PVC PLINTH PROFILE WOODCOLOR



No.	Tested component(s)
1	PVC, plastic, grey without wood motive
2	Wood covering, plastic, brown/beige
3	Elastic plastic, grey

## Phthalates in %

Test method: 12.01.02.04\_Phthalates (2021-08)

Substance name	Abbrev.	CAS-No.	LOQ	CS 1+2+3
Diisobutylphthalate <sup>1</sup>	DIBP	84-69-5	0.005	n.d.
Dibutylphthalate <sup>1</sup>	DBP	84-74-2	0.005	n.d.
Benzylbutylphthalate <sup>1</sup>	BBP	85-68-7	0.005	n.d.
Bis-(2-ethylhexyl)phthalate <sup>1</sup>	DEHP	117-81-7	0.005	n.d.
Di-n-octylphthalate	DNOP	117-84-0	0.005	n.d.
Diisononylphthalate	DINP	28553-12-0 68515-48-0	0.01	n.d.
Diisodecylphthalate	DIDP	26761-40-0 68515-49-1	0.01	n.d.
1,2-Benzenedicarboxylic acid, di-C6-8-branched alkyl esters, C7-rich <sup>2</sup>	DIHP	71888-89-6	0.02	n.d.
Bis(2-methoxyethyl)phthalate <sup>2</sup>	DMEP	117-82-8	0.005	n.d.
Diisopentylphthalate <sup>2</sup>	DIPP	605-50-5	0.005	n.d.
Dipentylphthalate <sup>2</sup>	DPP	131-18-0	0.005	n.d.
Di-n-hexyl-phthalate <sup>2</sup>	DNHP	84-75-3	0.005	n.d.
1,2-Benzenedicarboxylic acid, dipentylester, branched and linear	--	84777-06-0	0.02	n.d.
Di-cyclo-hexyl-phthalate	DCHP	84-61-7	0.005	n.d.
N-pentyl-isopentylphthalate	PIPP	776297-69-9	0.02	n.d.
1,2-Benzenedicarboxylic acid, di-C7-11-branched and linear alkyl esters	DHNUP	68515-42-4	0.02	n.d.
1,2-Benzenedicarboxylic acid, branched and linear dihexyl ester	--	68515-50-4	0.02	n.d.
Di-iso-hexylphthalate	DIHxP	71850-09-4	0.02	n.d.
1,2-benzenedicarboxylic acid, di-C6-10-alkyl esters; 1,2-benzenedicarboxylic acid, mixed decyl and hexyl and octyl diesters	--	68515-51-5 68648-93-1	0.02	n.d.

<sup>1</sup> Limit for articles: 0.1% Sum of 4 phthalates

<sup>2</sup> Limit for textile/ shoe articles: 1000 mg/kg

## Lead after total digestion in mg/kg

Test method:

Digestion: Microwave HNO<sub>3</sub>/H<sub>2</sub>O<sub>2</sub>

Measurement: ICP-OES: DIN EN ISO 11885:2009-09

LOQ = Limit of quantification

Substance name	CAS No.	LOQ	CS 1+2+3
Lead (Pb)	7439-92-1	10	100

**Conclusion:**

The sample is considered as marketable regarding the tested parameters (based on Regulation (EC) 1907/2006).

---

**General note:**

This report has been prepared for the titled project or named part thereof and should not be relied upon or used for any other project without an independent check being carried out as to its suitability and prior written authority of Intertek being obtained. Intertek accepts no responsibility or liability for the consequences of this document being used for a purpose other than the purposes for which it was commissioned. Any person using or relying on the document for such other purposes agrees, and will by such use or reliance be taken to confirm his agreement to indemnify Intertek for all loss or damage resulting therefrom. Intertek accepts no responsibility or liability for this document to any party other than the person by whom it was commissioned.

We would like to point out, that Intertek can't provide legally binding assessments referring to isolated cases. The individual legal advice in Germany is reserved to the legal advisory professions and a binding interpretation is subject to the court of justice.

Copying excerpts or otherwise reproducing parts of the test report is permitted only with the consent of the laboratory accepting the order. This report pertains only to the test item(s).

All testing requests are subject to our Terms and Conditions available on [www.intertek.com](http://www.intertek.com).

END OF REPORT